



TEST PANEL

Manufacturer : DAW TECH
Size : 12 x 12 in.
Thicknesses : 1.895, 1.912, 1.901, 1.861 in.
Avg. Thick. : 1.892 in.
Description : PROPRIETARY.

Sample No. : TEST-4 (50APM2)
Weight : 28.38 lbs.
Hardness : NA
Plies/Laminates : NA

Date Rec'd. : 05/16/11
Via : UPS
Returned : N/A

SET-UP

Shot Spacing : PER CUSTOMER REQUEST
Witness Panel : 0.020", 2024-T3 ALUMINUM
Obliquity : 0 deg.
Backing Material : NA
Conditioning : AMBIENT

Primary Vel. Screens : 6.5 ft., 9.5 ft.
Primary Vel. Location : 8.0 ft. From Muzzle
Residual Vel. Screens : NA
Residual Vel. Location : NA
Range to Target : 50.0 ft.
Target to Wit. : 6.0 in.

Range No. : 6
Temp. : 70 F
BP : 29.40 in. Hg
RH : 70%
Barrel No./Gun : 50-09
Gunner : T.CONTRERAS
Recorder : MASON

AMMUNITION

- (1) : CAL. .50 AP, M2, 708 gr.
- (2) :
- (3) :
- (4) :

Lot No. : UNKNOWN
Lot No. :
Lot No. :
Lot No. :

APPLICABLE STANDARDS OR PROCEDURES

- (1) : PER CUSTOMER REQUEST
- (2) :
- (3) :

Shot No.	Ammo.	Time 1 (usec)	Velocity 1 (ft/s)	Time 2 (usec)	Velocity 2 (ft/s)	Avg. Vel. (ft/s)	Vel. Loss (ft/s)	Strike Vel. (ft/s)	Penetration	Footnotes
1	1	1052	2852	1053	2849	2850	17	2833	None	

REMARKS :

FOOTNOTES :